

BESTNYL SE15VI01A

Polyamide 6,6 natural lubricated with 15% glass fibre reinforcement, for pieces that require good technical and mechanical properties, applied to any injection piece.

	Standard	Unit	Values	
			Dry	Conditioned
Generals				
Density	ISO 1183	gr /cm3	1,24	-
Melt Flow Index	ISO 1133	gr /10 min.	-	-
Humidity Pelets	ISO 1110	%	0,2	-
Hardness	SHORE D	Points	80	-
Mold Shrinkage	-	%	~0,7	-
Mechanical				
Tensile Strength	ISO 527	N /mm2	125	-
Elongation at break	ISO 527	%	4	-
Tensile Modulus	ISO 527	N /mm2	6500	-
Charpy Impact	23 °C ISO 179	Kj / m2	43	-
	-40 °C ISO 179	Kj / m2	-	-
Charpy notched Impact	23 °C ISO 179	Kj / m2	7	-
	-40 °C ISO 179	Kj / m2	-	-
Electrical				
Surface Resistivity	IEC 93	Ohm	10 ¹⁴	-
Dielectric strength	IEC 243	Kv / mm	32	-
Tracking Index (C.T.I.)	IEC 112	Kv / mm	-	-
Thermal				
Deflection Temp.Under Load (H.D.T.)	0,4 N ISO 75 /A	°C	250	-
	1,8 N ISO 75 /A	°C	230	-
VICAT Temperature	ISO 306	°C	255	-
Others				
UL-94 Flammability	UL-94	-	HB	-
Glow Wire	IEC 695	°C	-	-
Flammability speed	FMV 302	mm / min.	<100	-
Ashes	Triesa Test	%	15	-
Water absorption (24h) Lubrificated	ISO 62	%	~1	-
			YES	-
Processing				
Drying Material	2h - 4h 90 °C			
Mold. Temperature	70 °C - 80 °C			
Processing Temperature	270 °C - 275 °C			

-This values provided in this data sheet corresponds to our Knowledge. All products must be subjected to in company test by the user before application

-These data may not valid such material used in combination with any other materials or additives or in any process

- UL mesurements are doing in our lab according this norm

Source: Triesa Quality Control, Last Update: 16/03/2012

Please contact with us for any other Information.

*Bestnyl is a trademark of Triesa Poliamidas S.A.
© 1990 - 2013 Triesa Poliamidas S.A.

