

BESTNYL SE60VI01AH

**Polyamide 6.6 natural lubricated with 60% glass fibre reinforcement and heat stabilized,
High performance material for secure or critical pieces that require high mechanical properties.**

	Standard	Unit	Values	
			Dry	Conditioned
Generals				
Density	ISO 1183	gr /cm3	1,70	-
Melt Flow Index	ISO 1133	gr /10 min.	-	-
Humidity Pelets	ISO 1110	%	0,2	-
Hardness	SHORE D	Points	83	-
Mold Shrinkage	-	%	-	-
Mechanical				
Tensile Strenght	ISO 527	N /mm2	260	-
Elogantion at break	ISO 527	%	2	-
Tensile Modulus	ISO 527	N /mm2	16000	-
Charpy Impact	23 °C ISO 179	Kj / m2	95	-
	-40 °C ISO 179	Kj / m2	-	-
Charpy notched Impact	23 °C ISO 179	Kj / m2	17	-
	-40 °C ISO 179	Kj / m2	-	-
Electrical				
Surface Resistivity	IEC 93	Ohm	10 ¹⁵	-
Dielectric strenght	IEC 243	Kv / mm	35	-
Tracking Index (C.T.I.)	IEC 112	Kv / mm	450	-
Thermal				
Deflection Temp.Under Load (H.D.T.)	0,4 N ISO 75 /A	°C	255	-
	1,8 N ISO 75 /A	°C	-	-
VICAT Temperature	ISO 306	°C	>260	-
Others				
UL-94 Flammability	UL-94	-	HB	-
Glow Wire	IEC 695	°C	-	-
Flammability speed	FMV 302	mm / min.	<100	-
Ashes	Triesa Test	%	60	-
Water absorption (24h)	ISO 62	%	~0,5	-
Heat Stabilized			YES	-
Processing				
Drying Material	2h - 4h 100 °C			
Mold. Temperature	90 °C - 100 °C			
Processing Temperature	275 °C - 290 °C			

-This values provided in this data sheet corresponds to our Knowledge. All products must be subjected to in company test by the user before application

-These data may not valid such material used in combination with any other materials or additives or in any process

- UL measurements are doing in our lab according this norm

Source: Triesa Quality Control, Last Update: 20/01/2014

Please contact with us for any other Information.

*Bestnyl is a trademark of Triesa Poliamidas S.A.
© 1990 - 2014 Triesa Poliamidas S.A.

