

Acetal copolymer resin natural standard of MFI 9 and lubricated to improve injection and moulding process, is appropriate for any injection technical piece of general applications.

TECHNICAL DATA SHEET

		STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm ³	1,41	
	Melt Flow Index	ISO 1133	gr/10 min.	9	
	Humidity Pelets	ISO 1110	%	0,2	
	Hardness	SHORE D	Points	81	
	Mold Shrinkage	-	%	-	

		STANDARD	UNIT	DRY	CONDITIONED
MECHANICAL	Tensile Strenght	ISO 527	N/mm ²	64	
	Elogantion at break	ISO 527	%	65	
	Tensile Modulus	ISO 527	N/mm ²	2950	
	Charpy Impact	23 °C ISO 179	Kj/m ²	80	
		-40 °C ISO 179	Kj/m ²	-	
	Charpy Impact	23 °C ISO 179	Kj/m ²	6	
-40 °C ISO 179		Kj/m ²	-		

		STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	10 ¹⁶	
	Dielectric strength	IEC 243	Kv/mm	19	
	Tracking index (C.T.I.)	IEC 112	Kv/mm		

		STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	160	
		(H.D.T.)	1,8 N ISO 75/A	°C	110
	VICAT Temperatura	ISO 306	°C	165	

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in - any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

V3.00/2021

	STANDARD	UNIT	DRY	CONDITIONED
OTHERS	UL - Flammability	UL-94	-	HB
	Glow Wire	IEC 695	°C	-
	Fammability speed	FMV 302	mm/min.	<100
	Ashes	Triesa Test	%	-
	Water absorption (24h)	ISO 62	%	~0,2
	Lubricated			YES

RECOMMENDED VALUES

PROCESSING	Drying Material	2h - 4h 80-90°C
	Mold. Temperature	40°C-70°C
	Processing Temperature	180°C-200°C
	Back Temperature	170°C-185°C
	Middle Temperature	185°C-190°C
	Nozzle Temperature	190°C-205°C
	Hold Pressure	70 - 100 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

SOURCE: Triesa Quality Control; Last update: 15/05/2020