

PC/PBT Injection Molding Grade Impact modified, UV stabilized

TECHNICAL DATA SHEET

	STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm ³	1,21
	Melt Flow Index	ISO 1133	gr/10 min.	-
	Humidity Pelets	ISO 1110	%	0,2
	Hardness	SHORE D	Points	78
	Mold Shrinkage	-	%	~0,8

	STANDARD	UNIT	DRY	CONDITIONED
MECHANICAL	Tensile Strenth	ISO 527	N/mm ²	59
	Elogantion at break	ISO 527	%	>30
	Tensile Modulus	ISO 527	N/mm ²	2200
	Charpy Impact	23 °C ISO 179	Kj/m ²	NB
		-40 °C ISO 179	Kj/m ²	-
	Charpy Impact	23 °C ISO 179	Kj/m ²	48
-40 °C ISO 179		Kj/m ²	-	

	STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	-
	Dielectric strength	IEC 243	Kv/mm	35
	Tracking index (C.T.I.)	IEC 112	Kv/mm	-

	STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	110
		(H.D.T.)	1,8 N ISO 75/A	°C
	VICAT Temperatura	ISO 306	°C	128

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in - any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

V3.00/2021

	STANDARD	UNIT	DRY	CONDITIONED
OTHERS	UL - Flammability	UL-94	-	HB
	Glow Wire	IEC 695	°C	-
	Fammability speed	FMV 302	mm/min.	<100
	Ashes	Triesa Test	%	-
	Water absorption (24h)	ISO 62	%	~0,2
	UV stabilized			YES

RECOMMENDED VALUES

PROCESSING	Drying Material	3h - 4h 110°C
	Mold. Temperature	60°C-90°C
	Processing Temperature	250°C-270°C
	Back Temperature	240°C-250°C
	Middle Temperature	255°C-265°C
	Nozzle Temperature	270°C-275°C
	Hold Pressure	60 - 100 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

SOURCE: Triesa Quality Control; Last update: 12/05/2020