

**Copolyamide (PA 6/6.6) natural lubricated to gain improvements in injection and moulding Is an appropriate polyamide for any injection technique and general applications.**

TECHNICAL DATA SHEET

		STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm <sup>3</sup>	1,13	
	Melt Flow Index	ISO 1133	gr/10 min.	-	
	Humidity Pelets	ISO 1110	%	0,2	
	Hardness	SHORE D	Points	78	
	Mold Shrinkage	-	%	-	

		STANDARD	UNIT	DRY	CONDITIONED	
MECHANICAL	Tensile Strenght	ISO 527	N/mm <sup>2</sup>	73		
	Elogantion at break	ISO 527	%	~20		
	Tensile Modulus	ISO 527	N/mm <sup>2</sup>	2900		
	Charpy Impact	23 °C ISO 179		Kj/m <sup>2</sup>	-	
		-40 °C ISO 179		Kj/m <sup>2</sup>	-	
	Charpy Impact	23 °C ISO 179		Kj/m <sup>2</sup>	5	
-40 °C ISO 179			Kj/m <sup>2</sup>	-		

		STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	10 <sup>13</sup>	
	Dielectric strength	IEC 243	Kv/mm	-	
	Tracking index (C.T.I.)	IEC 112	Kv/mm	-	

		STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	205	
	(H.D.T.)	1,8 N ISO 75/A	°C	60	
	VICAT Temperatura	ISO 306	°C	-	

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in - any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

V3.00/2021

	STANDARD	UNIT	DRY	CONDITIONED
OTHERS	UL - Flammability	UL-94	-	HB
	Glow Wire	IEC 695	°C	-
	Fammability speed	FMV 302	mm/min.	<100
	Ashes	Triesa Test	%	-
	Water absorption (24h)	ISO 62	%	-
	Lubricated			YES

RECOMMENDED VALUES

PROCESSING	Drying Material	2h - 4h 100°C
	Mold. Temperature	50°C-80°C
	Processing Temperature	255°C-270°C
	Back Temperature	245°C-250°C
	Middle Temperature	255°C-265°C
	Nozzle Temperature	270°C-275°C
	Hold Pressure	60 - 100 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

SOURCE: Triesa Quality Control; Last update: 12/05/2020