

**Polyamide 6 black lubricated with V-0 free halogen quality and 15% charge mineral.**

		STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm <sup>3</sup>	1,23	
	Melt Flow Index	ISO 1133	gr/10 min.	-	
	Humidity Pelets	ISO 1110	%	0,2	
	Hardness	SHORE D	Points	78	
	Mold Shrinkage	-	%	-	

		STANDARD	UNIT	DRY	CONDITIONED
MECHANICAL	Tensile Strenth	ISO 527	N/mm <sup>2</sup>	70	
	Elogantion at break	ISO 527	%	7	
	Tensile Modulus	ISO 527	N/mm <sup>2</sup>	3500	
	Charpy Impact	23 °C ISO 179	Kj/m <sup>2</sup>	45	
		-40 °C ISO 179	Kj/m <sup>2</sup>	-	
	Charpy Impact	23 °C ISO 179	Kj/m <sup>2</sup>	4	
-40 °C ISO 179		Kj/m <sup>2</sup>	-		

		STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	10 <sup>13</sup>	
	Dielectric strength	IEC 243	Kv/mm	-	
	Tracking index (C.T.I.)	IEC 112	Kv/mm	-	

		STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	-	
		(H.D.T.)	1,8 N ISO 75/A	°C	-
	VICAT Temperatura	ISO 306	°C	-	

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in - any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

V3.00/2021

	STANDARD	UNIT	DRY	CONDITIONED
OTHERS	UL - Flammability	UL-94	-	V-0
	Glow Wire	IEC 695	°C	960
	Fammability speed	FMV 302	mm/min.	-
	Ashes	Triesa Test	%	~15
	Water absorption (24h)	ISO 62	%	-
	Flame Retardant, Free Hal.			YES

RECOMMENDED VALUES

PROCESSING	Drying Material	2h - 4h 100°C
	Mold. Temperature	60°C-90°C
	Processing Temperature	230°C-240°C
	Back Temperature	225°C-235°C
	Middle Temperature	240°C-245°C
	Nozzle Temperature	245°C-250°C
	Hold Pressure	50 - 90 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

SOURCE: Triesa Quality Control; Last update: 12/05/2020