

PBT natural with 20% glass fibre reinforcement and lubricated.

TECHNICAL DATA SHEET

	STANDARD	UNIT	DRY	CONDITIONED
GENERALS	Density	ISO 1183	gr/cm ³	1,45
	Melt Flow Index	ISO 1133	gr/10 min.	-
	Humidity Pelets	ISO 1110	%	0,2
	Hardness	SHORE D	Points	80
	Mold Shrinkage	-	%	-

	STANDARD	UNIT	DRY	CONDITIONED
MECHANICAL	Tensile Strenght	ISO 527	N/mm ²	115
	Elogantion at break	ISO 527	%	3
	Tensile Modulus	ISO 527	N/mm ²	7000
	Charpy Impact	23 °C ISO 179	Kj/m ²	57
		-40 °C ISO 179	Kj/m ²	-
	Charpy Impact	23 °C ISO 179	Kj/m ²	6
-40 °C ISO 179		Kj/m ²	-	

	STANDARD	UNIT	DRY	CONDITIONED
ELECTRICAL	Surface Resistivity	IEC 93	Ohm	10 ¹⁵
	Dielectric strength	IEC 243	Kv/mm	30
	Tracking index (C.T.I.)	IEC 112	Kv/mm	-

	STANDARD	UNIT	DRY	CONDITIONED
THERMAL	Deflection Temp. Under Load	0,4 N ISO 75/A	°C	215
		(H.D.T.)	1,8 N ISO 75/A	°C
	VICAT Temperatura	ISO 306	°C	>200

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in - any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

V3.00/2021

	STANDARD	UNIT	DRY	CONDITIONED
OTHERS	UL - Flammability	UL-94	-	HB
	Glow Wire	IEC 695	°C	-
	Fammability speed	FMV 302	mm/min.	<100
	Ashes	Triesa Test	%	~20
	Water absorption (24h)	ISO 62	%	~0,1
	Lubricated			YES

RECOMMENDED VALUES

PROCESSING	Drying Material	2h - 4h 110°C
	Mold. Temperature	70°C-90°C
	Processing Temperature	230°C-245°C
	Back Temperature	230°C-235°C
	Middle Temperature	240°C-245°C
	Nozzle Temperature	245°C-250°C
	Hold Pressure	40 - 70 Mpa

- The values provided in this data sheet correspond to our knowledge. All products must be subjected to in company test by the user before application.
- These datas do not release you from the obligation to test our products as to their suitability for the intended processes and final use.
- These data may not valid such material used in combination with any other materials or additives or in- any process.
- Triesa assumes no liability and makes no warranties of any kind, expressed or implied how to use this information data.
- UL measurements are done in our lab according to this norm.

SOURCE: Triesa Quality Control; Last update: 10/05/2020